



Exteriorguard™

Technical Data Sheet

ZS311Y28 Technical Data

Date : 06/11/2009

System	Color	Appearance	Gloss
Super durable	TRAFFIC YELLOW	Smooth	70 ± 4 units on 60°
Properties			
Specific Gravity	Approximately 1.66		
Coverage	116 sq. ft./lb/1 mil		
Hardness	2H - (ASTM D3363)		
Film thickness	Recommended film thickness 2.5 to 4 mils		
Salt Spray	1000 hrs less than 1/16" in creepage over B-1000 treated test panels (ASTM B117)		
Humidity	1000 hrs no blistering over B-1000 treated test panels (ASTM D2247)		
Flexibility	3/16" (ASTM D522)(Conical Mandrel)		
Impact	100 in-lb direct; 100 in-lb reverse (ASTM D2794)		
Cross Hatch Adhesion	5B (ASTM D3359)		
Curing Instructions	7 minutes at 400°F (204°C) or 10 minutes at 375°F (191°C) or 15 minutes at 350°F (177°C) (metal temperature)		
Features			
<ul style="list-style-type: none"> - Contributes to LEED credits - Enhanced mar resistance - Excellent outdoor durability (Meets or exceeds A.A.M.A. 2604) 			
Maximum Recommended Storage Temperature			80°F (27°C)